



APPALACHIAN GREEN

Technical Information

| | | |
|-------------|--------------------------------------|--------------|
| {ASTM C97} | Absorption by Weight, % | 0.08 |
| {ASTM C97} | Density, Lbs/CuFt | 170.4 |
| {ASTM C97} | Specific Gravity | 2.729 |
| {ASTM C170} | Compressive Strength, psi | 8580 |
| {ASTM C241} | Abrasion Resistance, Hardness | 11.3 |
| {ASTM C880} | Flexural Strength, psi | 1854 |
| {ASTM C99} | Modulus of Rupture, psi | 2029 |

