



VERMONT VERDE CAVENDISH

Technical Information

(ASTM C97)	Absorption by Weight, %	0.05
(ASTM C97)	Density, Lbs/CuFt	168
(ASTM C97)	Specific Gravity	2.690
(ASTM C170)	Compressive Strength, psi	41771
(ASTM C241)	Abrasion Resistance, Hardness	107.66
(ASTM C880)	Flexural Strength, psi	4178
(ASTM C99)	Modulus of Rupture, psi	3137



VERMONT
QUARRIES CORP.

Vermont Quarries Corporation. 7 US Route 4, Mendon, Vermont 05701

Phone: 802-775-1065 Fax 802-775-1369 e-mail: vtquarries@aol.com www.vermontquarries.com