



## EUREKA CALACATTA

### Technical Information

{ASTM C97}	<b>Absorption by Weight, %</b>	<b>0.06</b>
{ASTM C97}	<b>Density, lbs/CuFt</b>	<b>169.2</b>
{ASTM C97}	<b>Specific Gravity</b>	<b>2.711</b>
{ASTM C170}	<b>Compressive Strength, psi</b>	<b>9475</b>
{ASTM C241}	<b>Abrasion Resistance, Hardness</b>	<b>12.1</b>
{ASTM C880}	<b>Flexural Strength, psi</b>	<b>1226</b>
{ASTM C99}	<b>Modulus of Rupture, psi</b>	<b>1077</b>

