



MONTCLAIR MARIPOSA

Technical Information

| | | |
|-------------|--------------------------------------|--------------|
| {ASTM C97} | Absorption by Weight, % | 0.06 |
| {ASTM C97} | Density, lbs/CuFt | 169.2 |
| {ASTM C97} | Specific Gravity | 2.711 |
| {ASTM C170} | Compressive Strength, psi | 9475 |
| {ASTM C241} | Abrasion Resistance, Hardness | 12.1 |
| {ASTM C880} | Flexural Strength, psi | 1226 |
| {ASTM C99} | Modulus of Rupture, psi | 1077 |

