



MONTCLAIR MARIPOSA

Technical Information

{ASTM C97}	Absorption by Weight, %	0.06
{ASTM C97}	Density, Lbs/CuFt	169.2
{ASTM C97}	Specific Gravity	2.711
{ASTM C170}	Compressive Strength, psi	9475
{ASTM C241}	Abrasion Resistance, Hardness	12.1
{ASTM C880}	Flexural Strength, psi	1226
{ASTM C99}	Modulus of Rupture, psi	1077

